

TECHNICAL SHEET



Article: **B1235A (EH) i-OMEGA EH**

Norm: **EN ISO 20345:2022 +A1:2024**

Safety Class: **SB E WPA PS CI FO SR**

Sole	S40 GREY
Weight, size 42:	575 g
Footwear height:	70 mm
Width:	11,5
Construction / Sole:	STROBEL; AirTech/Tpu-Skin injected insulating outsole
Anti-perforation insert	Fresh'n Flex EH (PS)
Insole:	
Footbed supplied:	Dry'n Air Comfort Plus EH
Other usable Footbeds (certified):	Dry'n air Omnia insulation

Entire footwear: protections

Component	Description	Value	Minimum Requirement	Norm
SlimCap toe-cap	Impact Resistance (200J)	14,5 mm	≥ 14,0 mm	5.3.2.3
	Compression Resistance (15 kN)	16,0 mm	≥ 14,0 mm	5.3.2.4
Outsole (SR)	Slip Resistance 20345:2022			
	•Ceramic + Det. - Heel	0,40	≥ 0,31	5.3.5.2
	•Ceramic + Det. + Forepart	0,41	≥ 0,36	5.3.5.2
	•Ceramic + Glycerin (SR) - Heel	0,34	≥ 0,19	6.2.10.1
	•Ceramic + Glycerin (SR) - Forepart	0,30	≥ 0,22	6.2.10.1
Fresh'n Flex EH (PS)	Puncture resistance. 20345:2022	1489 N	Average value ≥ 1100N; Single value ≥ 950N	6.2.1.1.4
Thermal insulation	Thermal insulation			
	• Decreased Insole Temp. (CI)	5,5 °C	≤ 10°C	6.2.3.2
Energy absorption (E)	Shock-absorption in the heel region	32 J	≥ 20 J	6.2.4
(EH)	Electric Hazard Resistant Footwear	0,7 mA	≤ 1,0 mA (18 kV at 60 Hz, 1 min)	ASTM F2412-18

Upper

Materials	Description	Value	Minimum Requirement	Norm
Nabutek suedeleather	Tear Strenght	225 N	≥ 120 N	5.4.3
	Tensile Strenght	17 N/mm²	≥ 15 N/mm²	5.4.4
	Water vapour permeability	8,8 mg/cm² h	≥ 0,8 mg/cm² h	5.4.6
	Water vapour coefficient	59,3 mg/cm²	≥ 15mg/cm²	5.4.6
	Chromium VI content (if leather)	Not detectable	Not detectable	6.11
	Water passed	0,0 g	≤ 0,2 g	6.3
	Water absorption	15 %	≤ 30%	6.3

Lining

Materials	Description	Value	Minimum Requirement	Norm
Hi-tech 3D fabric	Tear Strenght	51 N	≥ 15 N	5.5.1
	Abrasion resistance	• No dry hole	No holes before 51,200 cycles	5.5.2
		• No hole in humid environment	No holes before 25,600 cycles	5.5.2
	Water steam permeability	80,1 mg/cm² h	≥ 2,0 mg/cm² h	5.5.3

Sole				
Materials	Description	Value	Minimum Requirement	Norm
AirTech et Tpu Skin Anti-Fatigue insulating	Cleat height	4,0 mm	≥ 2,5 mm	5.8.1.3
	Tear Strenght	5,6 kN/m	≥ 5 kN/m	5.8.2
	Abrasion resistance	85 mm ³	≤ 250 mm ³	5.8.3
	Flexural resistance after 30,000 cycles	1.3 mm	≤ 4,0 mm	5.8.4
	Flexural resistance after 150,000 cycles (hydrolysis)	1,8 mm	≤ 6,0 mm	5.8.5
	Upper/outsole bond strenght	N/A	> 4 N/mm; ≥ 3 N/mm with sole tear*	5.8.6
	Hydrocarbon resistance FO (volume change)	1,7 %	≤ 12%	6.4.2

Issued by: Innovation Director Ing. Cataldo De Luca	Signature 
--	--

The content of this technical sheet is copyright of BASE PROTECTION Unipersonale Srl. Reproduction, even partial, of texts and / or images presented here is expressly forbidden.

Technical sheet subject to revision at the same time as the certificate is issued. Typographical errors excepted. BASE PROTECTION reserves the right to modify the content of the technical sheet.