

## TECHNICAL SHEET



Article:	<b>B1213B I-CYBER TOP</b>
Norm:	<b>UNI EN ISO 20345:2011</b>
Safety Class:	<b>S1P ESD SRC</b>
ESD protection of electronic components:	<b>CEI EN 61340-5-1:2016, CEI EN 61340-4-5:2018 and CEI EN 61340-4-3:2018</b>
Footwear height:	<b>Mod. B, H 130 mm (≥113 mm, Rif. EN 20345-5.2.2)</b>
Width:	<b>11,5</b>
Construction:	<b>STROBEL; CEMENTED BIDENSITY SOLE PU/TPU ESD</b>
Cleaning and maintenance:	Use only soft brushes and water. Do not use substances such as alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.
Suggested fields:	<b>Electronics (EPA=Electrostatic protected areas ESD), automotive, automated lines, building</b>

### ESD Protection (Electrostatic discharges) for electronic devices

#### Suitable for use in EPA areas (Electrostatic discharges protected area)

Component	Description	Value	Norm Requirements
Entire footwear	Total resistance footwear/ground (footwear worn on a metal ground)	1,65 x 10 <sup>7</sup> Ω	< 1,00 x 10 <sup>8</sup> Ω
	Sole electrical transversal resistance (footwear resistance)	2,27 x 10 <sup>7</sup> Ω	≤ 1,00 x 10 <sup>8</sup> Ω
	Chargeability	< 20 V	< 100 V

#### Entire footwear: protections

Component	Description	Value	Norm Requirements	EN 20345	
Composite SLIM CAP toe-cap	Impact resistance (200 J)	15,0 mm	≥ 14 mm	5.3.2.3	
	• Free height after impact				
Sole (SRC)	Compression resistance (15 kN)	17,0 mm	≥ 14 mm	5.3.2.4	
	• Free height after compression				
Sole (SRC)	Slip resistance				
	• SRA – Sole (entire sole)	0,50	≥ 0,32	5.3.5.4	
	• SRA – Heel (Angle of 7°)	0,48	≥ 0,28	5.3.5.4	
	• SRB – Sole (entire sole)	0,18	≥ 0,18	5.3.5.4	
Fresh'n Flex (P)	Puncture resistance	No perforation	≥ 1100 N	6.2.1.1.2	
					• SRB – Heel (Angle of 7°)
Footbed (A)	Antistatic properties	dry 3,62 x 10 <sup>8</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2	
		humid 1,46 x 10 <sup>7</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2	
Sole/Upper Heat (HI) Cold (CI)	Thermal insulation	Insole temperature increase	N/A	≤ 22°C	6.2.3.1
		Insole temperature decrease	N/A	≤ 10°C	6.2.3.2
Heel (E)	Shock-absorption in the heel region	29 J	≥ 20 J	6.2.4	
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm <sup>2</sup>	6.2.5	
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6	

#### Upper

Component	Description	Value	Norm Requirements	EN 20345
Sublimated technical fabric	Tear resistance	115 N	≥ 120 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm <sup>2</sup>	5.4.4
Sublimated technical fabric	Water steam permeability	2,1 mg/cm <sup>2</sup> h	≥ 0.8 mg/cm <sup>2</sup> h	5.4.6
	pH value	N/A	≥ 3,2	5.4.7
	Chromium VI	N/A	Not detectable	5.4.9
	Water passed	N/A	≤ 0.2 g	6.3
	Water absorption	N/A	≤ 30%	6.3

<b>Lining</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
3D Fabric	Tear resistance	47 N	≥ 15 N	5.5.1
	Abrasion resistance	<ul style="list-style-type: none"> <li>Dry : the surface shows no holes</li> <li>humid: the surface shows no holes</li> </ul>	No holes till 51.200 cycles	5.5.2
			No holes till 25.600 cycles	5.5.2
	Water steam release	21,1 mg/cm <sup>2</sup> h	≥ 2,0 mg/cm <sup>2</sup> h	5.5.3
	pH value	N/A	Not detectable	5.5.4
	Chromium VI	N/A	Not detectable	5.5.5

<b>Insole</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
Fresh'n Flex ESD	Thickness	3,7 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	102 mg/cm <sup>2</sup>	≥ 70 mg/cm <sup>2</sup>	5.7.3
	Water release	97%	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	Not detectable	5.7.5

<b>Removable footbed*</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
DRY'N AIR OMNIA ESD WEARECO	Thickness	3,5 ± 0,5 mm (tip)	N/A	5.5.1
	Ph value	N/A	Not detectable	5.5.2
	Water absorption	Permeable through the holes	Permeable or ≥ 70mg/cm <sup>2</sup>	5.5.3
	Water release	Permeable through the holes	Permeable or ≥ 80%	5.5.3
	Abrasion resistance	No damage	Dry No holes till 25.600 cycles Humid no holes till 12.800 cycles	5.5.4.2
	Chromium VI	N/A	Not detectable	5.7

\* Compatible with DRY'N AIR SCAN&FIT OMNIA and Dry'n AIR OMNIA ESD insoles

<b>Sole</b>					
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>	
PU Midsole	Sole thickness without profiles	6 mm	≥ 4 mm	5.8.1.1	
	Profiles height	3 mm	≥ 2,5 mm	5.8.1.3	
	Tear resistance	8,8 kN/m	≥ 8 kN/m	5.8.2	
	Abrasion resistance	<ul style="list-style-type: none"> <li>relative volume loss</li> </ul>	100 mm <sup>3</sup>	≤ 250 mm <sup>3</sup>	5.8.3
	Flexion resistance	<ul style="list-style-type: none"> <li>Notches increase after 30.000 cycles</li> </ul>	1,9 mm	≤ 4 mm	5.8.4
TPU ESD Outsole	Hydrolysis	<ul style="list-style-type: none"> <li>Notches increase after 150.00 cycles</li> </ul>	2,2 mm	≤ 6 mm	5.8.5
	Outsole – insole detachment	4,7	≥ 4 N/mm; (* ) ≥ 3 N/mm with sole ripping	5.8.6	
	(HRO) Contact heat resistance (300°C)	No damage	No damage (melting, breaking)	6.4.1	
	(FO) Fuel resistance (volume changes)	2,7 %	≤ 12%	6.4.2	

Date: 02/04/2021

Copy in accordance with the Italian sheet